



Technical Data Sheet

Solef[®] 6008

polyvinylidene fluoride

Solef[®] 6008 PVDF homopolymer is a low-viscosity PVDF resin and is typically processed by injection molding.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Homopolymer • Low Viscosity	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.75 to 1.80		ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/2.16 kg	5.5 to 11	g/10 min	
230°C/5.0 kg	16 to 30	g/10 min	
Molding Shrinkage - Flow	2.0 to 3.0	%	
Water Absorption (24 hr, 23°C)	< 0.040	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ¹ (23°C, 2.00 mm)	1800 to 2500	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield, 23°C, 2.00 mm	50.0 to 60.0	MPa	
Break, 23°C, 2.00 mm	30.0 to 50.0	MPa	
Tensile Elongation ²			ASTM D638
Yield, 23°C, 2.00 mm	5.0 to 10	%	
Break, 23°C, 2.00 mm	20 to 300	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.15 to 0.35		
vs. Itself - Static	0.20 to 0.40		
Taber Abrasion Resistance			ASTM D4060
1000 Cycles, 1000 g, CS-10 Wheel	5.00 to 10.0	mg	

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength ³			ASTM D6110
23°C, 4.00 mm	40.0 to 120	J/m	

Hardness	Typical Value	Unit	Test method
Durometer Hardness (Shore D, 1 sec, 2.00 mm)	73 to 80		ASTM D2240

Solef® 6008

polyvinylidene fluoride

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	-40.0	°C	ASTM D4065
Vicat Softening Temperature	135 to 145	°C	ASTM D1525 ⁴
Melting Temperature	170 to 175	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	134 to 144	°C	ASTM D3418
CLTE - Flow (0 to 40°C)	1.4E-4	cm/cm/°C	ASTM D696
Specific Heat			ASTM E968
23°C	1200	J/kg/°C	
100°C	1600	J/kg/°C	
Thermal Conductivity (23°C)	0.20	W/m/K	ASTM C177
Crystallization Heat	54.0 to 60.0	J/g	ASTM D3417
Heat of Fusion	58.0 to 67.0	J/g	ASTM D3417

Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (23°C, 1.00 mm)	20 to 25	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 kHz)	7.00 to 10.0		ASTM D150

Flammability	Typical Value	Unit	Test method
Flame Rating (0.200 mm)	V-0		UL 94
Oxygen Index (3.00 mm)	44	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ Type IV, 1.0 mm/min

² Type IV, 50 mm/min

³ 2 m/s

⁴ Rate A (50°C/h), Loading 2 (50 N)

Solef® 6008

polyvinylidene fluoride



Progress beyond

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2023 Solvay Specialty Polymers. All rights reserved.